

DESCRIPTION

Johnstone's Trade Smooth Masonry is a durable coating, suitable for most exterior masonry surfaces and is shower resistant after 20 minutes at 23° c, and applied at 2°c and rising The durable film is tough, offering excellent resistance against dirt and grime and protects against atmospheric pollution.

RECOMMENDED USES



Suitable for external use on concrete, cement rendering, brick, stone, blockwork etc.

COLOUR RANGE

Brilliant White and Tintable.

FINISH

Matt

VOLUME SOLID

37.7%

COVERAGE



Up to 17m² per litre depending on the nature and porosity of the surface.

DRYING TIME



Touch Dry 1 hour
Rain resistant after 20 minutes at 23°c
Recoat after 2-4 hours.

TRANSPORTATION & STORAGE

PROTECT FROM FROST

To avoid the risk of spillage, always store and transport in a secure upright position.

Lift with care - gross weight does not exceed 8 kilograms (5L) / 15 kilograms (10L)

THINNER

Clean water.

VOC CONTENT

LOW VOC CONTENT 0.30-7.99%

VOCs (Volatile Organic Compounds) contribute to atmospheric pollution.

EU limit value for this product (Cat A/c):40g/l (2010).

This product contains max 10g/l VOC.

FILM THICKNESS

Wet: 100µm, dry: 30µm.

KEY PROPERTIES

- Rain resistant after 20 minutes*
- Application at 2°c and rising
- All season application
- 15+ years life expectancy
- Excellent colour retention and opacity

* at 23°C and 50% humidity

PREPARATION

All surfaces to be painted should be clean, dry and free from loose and flaking material including dirt and grease. Treat any mould or lichen with Sterilization Wash as directed.

Johnstone's Smooth Masonry can be applied directly over bare surfaces (thinned 5% with clean water) and previously painted surfaces, provided these are clean, sound and firm.

Stabilize surfaces of a highly porous or friable nature with Johnstone's Stormshield Stabilizing Solution or Johnstone's Stormshield Quick Dry Stabilizing Solution as directed.

Remove any lime wash or distemper completely. Avoid the inhalation of dust. Wear a suitable face mask if creating dust. Repair cracks and defective areas and treat fungal or algal growth with Johnstone's Sterilization Wash as directed

For further information and free Johnstone's datasheets call 01924 354354.

APPLICATION



Ensure good ventilation during application and drying. Stir well before use. If more than one container of colour is to be used in the same area, intermix before use. Apply two full coats, allowing 2 to 4 hours between coats under normal drying conditions.

Do not apply in temperatures below 2°c or in damp conditions. Suitable for application by brush, roller, conventional and airless spray.

CLEANING



Remove as much product as possible from application equipment before cleaning. Replace lid firmly. Clean equipment immediately after use with warm soapy water and rinse thoroughly. Some local authorities have special facilities for the disposal of waste coatings. Do not empty product into drains or watercourses.

PRECAUTIONS

- Contains reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one (EC no.247-500-7) and 2-methyl-2H-isothiazol-3-one (EC no.220-239-6) (3:1) and 1,2-benzisothiazol-3(2H)-one. May produce an allergic reaction.
- If medical advice is needed, have product container or label at hand.
- Keep out of reach of children.
- Do not get in eyes, on skin, or on clothing.
- IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.
- IF ON SKIN: Wash with plenty of water. Do not use solvent thinners or White Spirit.
- IF SWALLOWED: Call a POISON CENTRE or doctor if you feel unwell.
- Dispose of contents/container to a waste disposal site in accordance with local/national regulations.
- Contains Biocidal Product: Mixture of CMIT/MIT (3:1)

SIZES

2.5L, 5L and 10L